

marglass 430

EN Flame retardant FIBERGLASS fabric
 ES Tejido ignifugo de fibra de vidrio tipo E-GLASS

NON FLAMMABLE FABRIC



Technical Data Sheet

Composition	100% E-glass
Base	Fiberglass
Working side coating	none
Reverse side coating	none
Weave	Satin

Physical Properties

	Metric	US
Weight	430 gr/m ² ±5%	13 oz/yd ² ±5%
Thickness	0,4 mm	0,016 in
Width (contact us for especial widths)	150 cm ±2%	60 in
Roll lenght	50 mt	55 yd

Thermal Properties

	Metric	US
Continous temp	450 °C	835 °F
Peak temp	550 °C	1022 °F

Common Applications

- Flame barrier
- Thermal barrier
- Vertical curtains
- Fire blankets

Main Features



Flame Resistant

Technical Specs

	Results	Standard
Limited Flame Spread	A1 - A2	ISO 15025
Fire resistant level	M-0	UNE 23.102-90
Convective Heat	B1	ISO 9151
Tensile Strenght	Warp > 2700 N ±10% Weft > 1700 N ±10%	EN 13934-1

The described values in this technical sheet are the estimated results obtained in the MARINA TEXTIL S.L. internal laboratory according to standard methodologies. MARINA reserves the right to change the parameters without the obligation to notice it previously.
 Asbestos free product.

Maintenance Information

