

## marglass V1035

NON FLAMMABLE FABRIC



EN Flame retardant texturized FIBERGLASS fabric with vermiculite coating  
 ES Tejido ignífugo de fibra de vidrio tipo Eglass texturizado con tratamiento de vermiculita



### Technical Data Sheet

Composition	72% E-glass 28% Vermiculite
Base	Fiberglass
Working side treatment	Vermiculite
Reverse side treatment	Vermiculite
Weave	Plain

### Physical Properties

	Metric	US
Weight	1035 gr/m <sup>2</sup> ±5%	30 oz/yd <sup>2</sup> ±5%
Thickness	1,3 mm	0,051 in
Width <small>(contact us for especial widths)</small>	100 cm ±2%	39 in
Roll length	50 mt	55 yd

### Thermal Properties

	Metric	US
Continous temp	800 °C	1472 °F
Peak temp	1000 °C	1832 °F

### Common Applications

- Flame barrier
- Thermal barrier
- Vertical curtains
- Fire blankets
- Welding blanket

### Main Features



Flame Resistant



Abrasion resistant



Thermal resistant

### Technical Specs

	Results	Standard
Limited Flame Spread	A1 - A2	ISO 15025
Tensile Strenght	Warp > 4500 N ±10% Weft > 2500 N ±10%	ISO 4606

*The described values in this technical sheet are the estimated results obtained in the MARINA TEXTIL S.L. internal laboratory according to standard methodologies. MARINA reserves the right to change the parameters without the obligation to notice it previously. Asbestos free product.*

### Maintenancance Information

